



# Technical Data Sheet

## Bondloc B620 High Strength Retainer

### PRODUCT DESCRIPTION

B620 is designed for the bonding of cylindrical fitting parts. The product cures when confined in the absence of air between close fitting metal surfaces and prevents loosening and leakage from shock and vibration.

### APPLICATIONS

Typical applications include locating pins in radiator assemblies, sleeves into pump housings and bearings in auto transmissions. Particularly suitable for applications where temperature resistance up to 200°C is required.

### USEFUL NOTES

Where possible, remove thick deposits of grease or dirt, however B603 will penetrate the film once it has been tightened.

### INSTRUCTIONS FOR USE

Surface keying action is greatly increased by rough surface finish, giving higher shear strength. Ideal roughness is between 10-120 microns with a preferred tolerance of between 30-100 microns. The larger gaps over 175 microns can result in ultimate strength loss. Ensure parts are clean, dry and free from oil and grease.

### COMPATIBLE ACCELERATOR/PRIMER

Primers such as B7471 Anaerobic activator or the faster B7649 structural accelerator can be used, however up to 30% strength loss can occur when using accelerators.

### STORAGE

Store in a cool area out of direct sunlight.  
Shelf Life >18 months at 20°C.

### TECHNICAL FEATURES

Resin	Mod Urethane Acrylate
Colour	Green
Cure speed with activator	<5 mins on gaps
Cure speed without activator	5 mins
Viscosity Brookfield Sp3 @20rpm@25°C	8,500cps
Gap Fill	0.2mm
Flash Point	>85°C
Shelf Life	18 months
Specific Gravity	1.08
Temperature Range	-55°C to +230°C

### TYPICAL BOND CHARACTERISTICS

Full Cure Time	24 hours
Shear Strength	>26N/mm <sup>2</sup>
Fast hold	5-7 mins @ 25°C
Short ultimate cure	<6 hours

### HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

### PACKAGING FORMAT

Bottles.....10ml,25ml,50ml,250ml  
Clam Packs.....10ml,25ml,50ml

Bondloc UK Ltd.  
Units 1 & 2  
Bewdley Business Park  
Bewdley, Worcestershire  
DY12 2TZ, UK

+44 (0) 1299 269 269  
sales@bondloc.co.uk

**PRECAUTIONS:** This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

