



Technical Data Sheet

Bondloc B641 Bearing Fit Retainer

PRODUCT DESCRIPTION

Bearing Fit B641 is a single part Anaerobic securing compound, designed for fitting cylindrical metal assemblies and cures when confined between the parts.

APPLICATIONS

B641 will secure all types and sizes of Bearings, Shafts and Cylindrical parts which will require disassembly in the future. B641 is of medium strength and is colour coded yellow for job identification.

USEFUL NOTES

Where cure speed is long, acceptable bond times can be obtained by treating the parts with B7471 activator or by using the faster B7649 accelerator.

PROPERTIES

Fast fixture, usually under 15 minutes
 Medium strength removable compound
 Typical strength 12N/mm²

INSTRUCTIONS FOR USE

Ensure parts are clean, dry and free from oil and grease.

COMPATIBLE ACCELERATOR/PRIMER

Primers such as B7471 (Standard Anaerobic activator) or the faster B7649 structural accelerator can be used, however up to 30% strength loss can occur when using accelerators.

STORAGE

Store in a cool area out of direct sunlight.
 Shelf Life >18 months at 20°C.

TECHNICAL FEATURES

Resin	Mod. Dimethacrylate
Colour	Yellow
Fixture speed with activator	<5 mins
Fixture speed without activator	10-15 mins
Viscosity Brookfield Sp3 @20rpm@25°C	400-800cps
Gap Fill	0.1mm
Flash Point	>100°C
Shelf Life	18 months
Specific Gravity	1.06
Temperature Range	-55°C to +150°C

TYPICAL BOND CHARACTERISTICS

Full Cure Time	12 hours
Shear Strength	>14N/mm ²

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS.

PACKAGING FORMAT

Bottles.....10ml,25ml,50ml,250ml
 Clam Packs.....10ml,25ml,50ml

Bondloc UK Ltd.
 Units 1 & 2
 Bewdley Business Park
 Bewdley, Worcestershire
 DY12 2TZ, UK
 +44 (0) 1299 269 269
 sales@bondloc.co.uk

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheets (SDS) for this and all other products being used are understood by all persons who will work with the product. Warranty: All products purchased from or supplied by Bondloc are subject to terms and conditions set out in the contract. Bondloc warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Bondloc is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Bondloc makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent.

